

TECHNICAL DATA SHEET



Validation date: 19/05/200

ISO 9001



STANDARD RANGE 1PURB55/LCW

CONVEYOR BELT TPU WHITE

Complies with FDA and EU regulations for conveying of foodstuff

CONSTRUCTION

1	1-ply polyester fabric
PUR	TPU polyurethan
B	Colour : white
55	Top cover thickness : 0,55 mm
LC	115N/mm fabric, rigid in weft, antistatic
W	Impregnated backside

MAIN TECHNICAL DATA


Top cover:	hardness: 85 Sh.A	surface: glossy, smooth
Total thickness:	1,15 mm	$\pm 0,1$ mm per ply
Weight per m²:	1 250 g	$\pm 10\%$
Friction Coefficient on steel slider bed:	0,20	$\pm 20\%$
Manufacturing width:	2 000 mm	
Temperatures:		
* Product temperature:	-40°C to +90°C	
* Ambient temperature:	-25°C to +60°C	
Type of support:	Slider bed	

MECHANICAL DATA

Tolerances: +20% -10%

Breaking load:	90 N/mm
Load for 1% extension:	7 N/mm
Maximum working tension:	10 N/mm

Pulley diameters:



These values are not linked to the requested \varnothing to pull the belt to rotation.

Ambient temperature:	from 0°C to +8°C: add +50%
	from 0°C to -25°C: add +100%

ENDLESS JOINTINGS

Top heating plate:	150°C $\pm 10^\circ$ C
Bottom heating plate:	130°C $\pm 10^\circ$ C
Time:	1 mn ± 1 mn
Pressure:	1,0 bar $\pm 0,5$ bar
Additional material (powder or film):	none

These recommendations may vary according to the equipment used and press heating system.

Splicing methods to be used:

DS (finger joint)



Fasteners: SL00 - SecuriG1

Accessories that may be fitted on this belt: None

These data are subject to modification. Please make sure of their validity.
REVEYRON S.A. should not be held responsible when the data sheet used is not valid anymore.

reveyron S.A.

247, route du Mas Rillier, Les Echets - 01700 MIRIBEL - France

Tél.: +33 (0)4 78 91 81 01

Fax: +33 (0)4 78 91 05 09

www.reveyron.com

E.mail: info@reveyron.fr