TECHNICAL DATA SHEET



Validation date: 07/05/2013

!Attention product homologated as a project!

CUSTOMIZED MANUFACTURING 1PURB25MAT/FW

CONVEYOR BELT TPU WHITE

Complies with FDA and EU regulations for conveying of foodstuff

CONSTRUCTION

1 1-ply polyester fabricPUR TPU polyurethanB Colour : white

25 Top cover thickness: 0,25 mm

MAT Mat finish

F 120N/mm fabric, flexible in weft

W Impregnated backside

MAIN TECHNICAL DATA

Top cover: hardness: 85 Sh.A surface: mat, smooth

Total thickness: $0.90 \text{ mm } \pm 0.1 \text{ mm per ply}$

Weight per m²: 950 g \pm 10% Friction Coefficient on steel slider bed: 0,20 \pm 20%

Manufacturing width: 2 000 mm

Temperatures:

* Product temperature: -40°C to +90°C * Ambient temperature: -25°C to +60°C

Type of support: Slider bed

MECHANICAL DATA

Tolerances: +20% -10%

Breaking load:90N/mmLoad for 1% extension:7N/mmMaximum working tension:10N/mm

Pulley diameters: (recommended as a minimum with a 20°C ambient temperature)

→

Minimum drive and tension: Ø 8 mm

Minimum reverse flexing: Ø 20 mm

These values are not linked to the requested \emptyset to pull the belt to rotation.

Tél.: +33 (0)4 78 91 81 01

Ambient temperature: from 0°C to +8°C: add +50%

from 0°C to -25°C: add +100%

ENDLESS JOINTINGS

Top heating plate: $150^{\circ}\text{C} \pm 10^{\circ}\text{C}$ Bottom heating plate: $150^{\circ}\text{C} \pm 10^{\circ}\text{C}$ Time: $1 \text{ mn} \pm 1 \text{ mn}$ Pressure: $2,0 \text{ bar } \pm 0,5 \text{ bar}$

Additional material (powder or film): none

These recommendations may vary according to the equipment used and press heating system.

Splicing methods to be used:

DS (finger joint)



Fasteners: SL00 - SECURI-G001

Accessories that may

be fitted on this belt: None

These data are subject to modification. Please make sure of their validity. REVEYRON S.A. should not be held responsible when the data sheet used is not valid anymore.

reveyron S.A.

247, route du Mas Rillier, Les Echets - 01700 MIRIBEL - France

Fax: +33 (0)4 78 91 05 09 www.reveyron.com

E.mail: info@reveyron.fr