



TECHNICAL DATASHEET

ON-DEMAND MANUFACTURING 2PURX55HR/CW

Conveyor belt TPU Polyurethane BLUE Complies with EU regulations for conveying foodstuff

DESCRIPTION

2 2-ply polyester fabric TPU Polyurethane **PUR** Colour: blue RAL 5015 X

Top cover thickness: 0,55 mm 55

HR "Rice grain" positive pattern, easy to clean

80 N/mm fabric, rigid in weft W Impregnated bottomside

MAIN TECHNICAL DATA

Top cover: Hardness 93 ShA [HR] "Rice grain" pattern

Total thickness: 1,70 mm ± 0,1 mm per ply

Weight per m^2 : 1 800 g ± 10% Manufacturing width: 2 000 mm

Product temperature: -40°C to +90°C Ambient temperature: -25°C to +60°C

Type of support: Slider bed -

Coefficient of friction (on steel slider bed): 0,20 ± 20%

MECHANICAL STRENGTHS

Tolerances: -10% +20%


Tensile strength: 120 N/mm

Tensile force for 1% elongation (k1%): 10 N/mm

Maximum working tension: 15 N/mm

MINIMUM PULLEY DIAMETERS

(at 20°C ambient temperature)




Working conditions:

- from 0°C to +8°C: add +50% on min. pulley diameter
- from -25°C to 0°C: add +100% on min. pulley diameter

The minimum pulley diameter is not related to the diameter needed to achieve a friction drive.

SPLICING OPTIONS


DS Round finger single splice 50 x 20 mm




DSP Narrow single finger splice 70 x 10 mm



DS/DEC Round finger overlapped splice



SF/PE Straight or Diagonal single overlap splice



PRESS SETTINGS

These recommendations may vary according to the equipment and press heating svstem.

Top heating platen (± 10°C): 160°C Bottom heating platen (± 10°C): 140°C

Welding Time (± 1 min): 2 min Pressure (± 0,5 bar): 2,0 bar

Reveyron does not recommend using foil for splicing.

FASTENERS / LACING

Securi-P2 (inox, flat wires) - SL01 (inox, self-lock) -

BELT FABRICATION

This belt material can be fitted with: V-guides / Profiles / Cleats / Corrugated sidewalls /

These data may change. The client remains liable for the proper choice of the belt material. Reveyron cannot be held responsible for any damage caused by improper use of the belt material.

