

# **TECHNICAL DATASHEET**

### STANDARD RANGE 2PURX55HRX/CW

## **Conveyor belt TPU Polyurethane BLUE**

#### DESCRIPTION

- 2 2-ply polyester fabric
- **TPU** Polyurethane PUR
- Colour: blue RAL 5015 Х
- Top cover thickness: 0,55 mm 55
- "Rice grain" positive pattern, easy to clean HR
- Blue inner ply Х
- 80 N/mm fabric, rigid in weft С
- Impregnated bottomside W

#### MAIN TECHNICAL DATA

Top cover: Hardness 93 ShA [HR] "Rice grain" pattern

Total thickness: 1,70 mm ± 0,1 mm per ply

Weight per m<sup>2</sup>: 1 800 g ± 10%

Manufacturing width: 2 000 mm

**Product temperature:** -40°C to +90°C

Ambient temperature: -25°C to +60°C

Type of support: Slider bed -

Coefficient of friction (on steel slider bed): 0,20 ± 20%

#### **MECHANICAL STRENGTHS**

Tolerances: -10% +20%


Tensile strength: 120 N/mm

Tensile force for 1% elongation (k1%): 10 N/mm

Maximum working tension: 15 N/mm

#### **MINIMUM PULLEY DIAMETERS**

(at 20°C ambient temperature)



25 mm

Reverse flexing: 50 mm

Working conditions:


- from 0°C to +8°C: add +50% on min. pulley diameter
- from -25°C to 0°C: add +100% on min. pulley diameter

The minimum pulley diameter is not related to the diameter needed to achieve a friction drive.


Complies with EU regulations for conveying foodstuff

#### SPLICING OPTIONS


DS Round finger single splice 50 x 20 mm




DSP Narrow single finger splice 70 x 10 mm



DS/DEC Round finger overlapped splice



SF/PE Straight or Diagonal single overlap splice



PRESS SETTINGS These recommendations may vary according to the equipment and press heating svstem.

Top heating platen (± 10°C): 160°C

Bottom heating platen (± 10°C): 140°C

Welding Time (± 1 min): 2 min

Pressure (± 0,5 bar) : 2,0 bar

Reveyron does not recommend using foil for splicing.

#### **FASTENERS / LACING**

Securi-P2 (inox, flat wires) - SL01 (inox, self-lock) -

#### **BELT FABRICATION**

This belt material can be fitted with : V-guides / Profiles / Cleats / Corrugated sidewalls /

These data may change. The client remains liable for the proper choice of the belt material. Reveyron cannot be held responsible for any damage caused by improper use of the belt material.

REVEYRON SAS 247 route du Mas Rillier - Les Echets - 01700 MIRIBEL - FRANCE Light Conveyor Belts & Belt Bend Conveyors



Tel: +33 4 78 91 08 51 www.reveyron.com info@reveyron.com VAT FR54 769 201 187 art 286 ter du CGI - Capital 1 000 000 € - Siret 769 201 187 00010 - NAF 1396Z