



# TECHNICAL DATASHEET

## STANDARD RANGE 2PURB20I/PCW

Conveyor belt TPU Polyurethane WHITE Complies with EU regulations for conveying foodstuff

#### **DESCRIPTION**

2 2-ply polyester fabricPUR TPU PolyurethaneB Colour: white

20 Top cover thickness: 0,20 mm

Clear inner ply

PC 70N/mm fabric, rigid in weft, antistatic

W Impregnated bottomside

#### MAIN TECHNICAL DATA

**Top cover:** Hardness 85 ShA Smooth, glossy **Total thickness:** 1,25 mm ± 0,1 mm per ply

Weight per m²: 1 450 g ± 10%

Manufacturing width: 2 000 mm

Product temperature: -40°C to +90°C

Ambient temperature: -25°C to +60°C

Type of support: Slider bed -

Coefficient of friction (on steel slider bed):  $0.20 \pm 20\%$ 

## **MECHANICAL STRENGTHS**

Tolerances: -10% +20%


Tensile strength: 110 N/mm

Tensile force for 1% elongation (k1%): 8 N/mm

Maximum working tension: 15 N/mm

## **MINIMUM PULLEY DIAMETERS**

(at 20°C ambient temperature)



#### Working conditions:

- from 0°C to +8°C: add +50% on min. pulley diameter
- from -25°C to 0°C: add +100% on min. pulley diameter

The minimum pulley diameter is not related to the diameter needed to achieve a friction drive.

## **SPLICING OPTIONS**


DS Round finger single splice 50 x 20 mm




DSP Narrow single finger splice 70 x 10 mm



DS/DEC Round finger overlapped splice



SF/PE Straight or Diagonal single overlap splice



## PRESS SETTINGS

These recommendations may vary according to the equipment and press heating system.

Top heating platen (± 10°C): 160°C

Bottom heating platen (± 10°C): 145°C

Welding Time (± 1 min): 2 min Pressure (± 0,5 bar): 2,0 bar

Reveyron does not recommend using foil for splicing.

#### **FASTENERS / LACING**

Securi-P1 (inox, flat wires) - SL00 (inox, self-lock) -

### **BELT FABRICATION**

This belt material can be fitted with: V-guides / Profiles / Cleats / Corrugated sidewalls /

These data may change. The client remains liable for the proper choice of the belt material. Reveyron cannot be held responsible for any damage caused by improper use of the belt material.

