TECHNICAL DATA SHEET



ISO 9001

CUSTOMIZED MANUFACTURING CONVEYOR BELT TPU WHITE 2PURBD30/CW

1,70 mm ± 0,1 mm per ply

±20%

Tolerances: +20% -10%

120 N/mm 10 N/mm

15 N/mm

1 600 g ± 10%

-40°C to +90°C

-25°C to +60°C

0,20

2 000 mm

Slider bed

(recommended as a minimum with a 20°C

Minimum drive and tension:

ambient temperature)

Ø 20 mm

Minimum reverse flexing: Ø 50 mm

Complies with FDA and EU regulations for conveying of foodstuff

CONSTRUCTION

- 2-ply polyester fabric 2
- PUR TPU polyurethan
- Colour : white В
- Diamond pattern on running side D
- Top cover thickness : 0,55 mm 30

Friction Coefficient on steel slider bed:

80N/mm fabric, rigid in weft, antistatic С

Top cover: hardness: 85 Sh.A surface: diamond profile

W Impregnated backside

MAIN TECHNICAL DATA

Total thickness:

Manufacturing width:

* Product temperature:

* Ambient temperature:

MECHANICAL DATA

Load for 1% extension:

Maximum working tension:

Weight per m²:

Temperatures:

Type of support:

Breaking load:

Pulley diameters:

ENDLESS JOINTINGS

Top heating plate:	165°C <i>± 10°</i> C
Bottom heating plate:	155°C ± 10°C
Time:	2 mn ± 1 mn
Pressure:	2,0 bar ± 0,5 bar
Additional material (powder or film):	none


These recommendations may vary according to the equipment used and press heating system.

Splicing methods to be used:


DS (finger joint)



PE (overlap joint)



DS/DEC (double finger joint)



SL01 - SécuriG001

Fasteners:

Accessories that may be fitted on this belt:

Except for some cases, this belt can t fitted out with : guiding profiles, cleats sidewalls

These values are not linked to the requested Ø to pull the belt to rotation.

Ambient temperature:

from 0°C to +8°C: add +50% from 0°C to -25°C: add +100%

Æ

These data are subject to modification. Please make sure of their validity. REVEYRON S.A. should not be held responsible when the data sheet used is not valid anymore.

reveyron S.A.

247, route du Mas Rillier, Les Echets - 01700 MIRIBEL - France

Tél.: +33 (0)4 78 91 81 01

Fax: +33 (0)4 78 91 05 09 www.reveyron.com

E.mail: info@reveyron.fr