Validation date: 02/12/2008

TECHNICAL DATA SHEET



STANDARD RANGE 2PURB90/LW

CONVEYOR BELT TPU WHITE

Complies with FDA and EU regulations for conveying of foodstuff

CONSTRUCTION

2-ply polyester fabric 2 **PUR** TPU polyurethan В Colour: white

90 Top cover thickness: 0.90 mm 125 N/mm fabric, rigid in weft L

Impregnated backside W

MAIN TECHNICAL DATA

hardness: 85 Sh.A Top cover: surface: glossy, smooth

0,122" ± 0,0039 " per ply Total thickness:

Weight per Sq Ft: 0,74 lbs ± 10% Friction Coefficient on steel slider bed: 0,20 ± 20%

Manufacturing width: 78,74"

Temperatures:

-40°F to +194°F * Product temperature: -13°F to +140°F * Ambient temperature:

Slider bed Type of support:

+20% -10% Tolerances: **MECHANICAL DATA**

Breaking load: 1 142 lbs/in. lbs/in. Load for 1% extension: 74 Maximum working tension: lbs/in. 114

(recommended as a minimum with a 70°F **Pulley diameters:**

ambient temperature)

Minimum drive and tension: Ø 3,15" Minimum reverse flexing: Ø 4,33"

These values are not linked to the requested Ø to pull the belt to rotation.

Ambient temperature: from 32°F to +46°F: add +50%

from 32°F to -13°F: add +100%

ENDLESS JOINTINGS

Top heating plate: 302°F ± 20°F Bottom heating plate: 302°F ± 20°F Time: 2 mn ± 1 mn Pressure: 29 psi ± 7 psi

Additional material (powder or film): none

These recommendations may vary according to the equipment used and press heating system.

Splicing methods to be used:

DS (finger joint)



PΕ step overlap

DS/DEC (double finger joint)



Fasteners: SL02 - Sécura 02 - Sécurinox 2

- Minibelt - Airport

Accessories that may be fitted on this belt:

Except for some cases, this belt can be fitted out with : quiding profiles, cleats, sidewalls

These data are subject to modification. Please make sure of their validity.

REVEYRON S.A. should not be held responsible when the data sheet used is not valid anymore.

reveyron S.A.

247, route du Mas Rillier, Les Echets - 01700 MIRIBEL - France

Tel.: +33 4 78 91 81 01 Fax: +33 4 78 91 05 09 www.reveyron.com E.mail: info@reveyron.com